## Off the Grid 1233

**Flame** 1310

## **Specifications**

#### **Contents**

49% pre-consumer recycled polyester 38% post-consumer recycled polyester 13% polyester

#### Weight

 $10.0 \pm 1.0$  oz./lin. yd.

#### Width

66" min. useable

#### Repeat

none

#### **Treatment**

polyester binder

#### Backing

none

#### **Treatment**

polyester binder

### **Cleaning Code**

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

#### **Performance**









#### **Breaking Strength (ASTM D5034)**

185 lbf min. warp and 165 lbf min. fill

#### Tear (ASTM D2261)

25 lbf min. warp and fill

#### Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

#### Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

#### **Flammability**

ASTM E84 Class I or A

#### NRC of anechoic termination

1.00

#### NRC of fabric in front of anechoic termination

1.00

#### **Miscellaneous**

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.





This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.



The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

# Acoustical Performance for Panel Applications (ISO 10534-2)

