# Synopsis 2136

**Butterscotch** 1213

# **Specifications**

#### Contents

52% post-consumer recycled polyester 48% pre-consumer recycled polyester

#### Weight

 $10.6 \pm 1.0$  oz./lin. yd.

#### Width

54" min. useable

#### Repeat

7.25" vertical | 4.25" horizontal Random match

#### **Treatment**

none

#### Backing

none

# **Cleaning Code**

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May be cleaned with 10% bleach-to-water solution. Rinse well after cleaning. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners. Read the <a</p>

href="https://www.guilfordofmaine.com/system/res/28/original/Guilford\_of\_Maine\_-\_Cleaning\_\_Disinfection\_Handbook.pdf?1596642657" target="\_blank">Cleaning & amp; Disinfection Handbook</a>.

## **Performance**











# **Breaking Strength (ASTM D5034)**

295 lbf min. warp and 180 lbf min. fill

## Tear (ASTM D2261)

min. warp and fill

## Seam Slippage (ASTM D4034)

115 lbf warp and 110 lbf fill

## Pilling resistance (ASTM D3511)

Class 4

# Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

# Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

#### Wyzenbeek Abrasion resistance (ASTM D4157)

100,000 double rubs cotton duck

## Flammability


CA Technical Bulletin 117-2013 Section 1 ASTM E84 Class I or A

## NRC of anechoic termination

1.00

## **Miscellaneous**

Proudly woven in North America supporting our local communities. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.





Terratex is a registered trademark of Duvaltex and designates fabrics that are made from 100% recycled or compostable material using increasingly sustainable manufacturing practices to produce a high quality product that is recyclable at the end of its useful life.



This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.



# NRC of fabric in front of anechoic termination

.90

# Acoustical Performance for Panel Applications (ISO 10534-2)

