# **Amaze** 2139

Bone 1262

# **Specifications**

#### Contents

82% polyester 18% post-consumer recycled polyester

Weight 12.9 +/- 1.0 oz./lin. yd.

Width 66" min. usable

Repeat 11.7" vertical | 12.8" horizontal Random match

Treatment

Backing

# **Cleaning Code**

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

## Performance







Breaking Strength (ASTM D5034) 290 lbf min. warp and 230 lbf min. fill

**Tear (ASTM D2261)** 15 lbf min. warp and fill

Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours

Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet

Flammability ASTM E84 Class I or A

### Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.





This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.

