

Phrase 9508

Shale 3070

Specifications

Contents

100% post-consumer recycled polyester

Weight

12.6 ± 1.0 oz./lin. yd.

Width

54" min. useable

Repeat

1.1875" vertical | none horizontal

Treatment

none

Backing

acrylic backcoating

Backing

acrylic backcoating

Cleaning Code

<p>Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May be cleaned with a 10% bleach-to-water solution. Rinse well after cleaning. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners. Read the Cleaning & Disinfection Handbook</p>

Performance



Breaking Strength (ASTM D5034)

190 lbf min. warp and fill

Tear (ASTM D2261)

10 lbf min. warp and 20 lbf min. fill

Seam Slippage (ASTM D4034)

60 lbf warp and fill

Pilling resistance (ASTM D3511)

Class 4 min.

Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 40 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Wyzenbeek Abrasion resistance (ASTM D4157)

100,000 double rubs cotton duck

Flammability

CA Technical Bulletin 117-2013 Section 1

Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended.

Colors may vary between dye lots. This is a directional fabric.

